

## 530 nm band PANDA

### Feature

- 530 nm band polarization maintaining fiber

### Common specifications

Concentricity error	≤ 0.5 μm
Cladding diameter	125 ± 1 μm (Major diameter)
Polarization crosstalk	≤ -30 dB/100m @ 630 nm
Beat length	≤ 2.0 mm @ 630 nm
Minimum bending radius	1% proof : R30 mm 2% proof : R20 mm*

### Product list

Product	Mode field diameter	Attenuation	Cutoff wavelength	Coating structure	Coating diameter	Specification number		
						---	ID	Rev
SM53-PS-H90D	4.2 ± 0.5 μm @ 630 nm	≤ 15 dB/km @ 630 nm	0.45 - 0.53 μm	UV curable acrylate /Polyester elastomer (Color : Black)	900 ± 100 μm	B-13D0086-3B-	1	0
SM53-PS-H90D-H						B-13D0086-3B-	2	0
SM53-PS-U40D				UV curable acrylate	400 ± 15 μm	B-13D0086-3B-	3	0
SM53-PS-U40D-H						B-13D0086-3B-	4	0

\*2% proof test type is available, and code '-H' is added at the end of the product name. (e.g. SM15-PS-U40D-H)



Optical Fiber Division  
1440, Mutsuzaki, Sakura, Chiba 285-8550, Japan

<http://www.fujikura.co.jp/>  
[optodevice@jp.fujikura.com](mailto:optodevice@jp.fujikura.com)

Specifications are subject to change without prior notice