TEC* SM fiber with heat resistant coating

* Thermally-diffused Expanded Core

Feature

- · 1310 and 1550 nm band TEC SM fiber
- · Thermally-diffused Expanded Core (TEC) technology is applied to SM fiber
- Temperature range is -40 and +150 deg C.
- · It is suitable for silicon photonics device

Product

TEC13-15-U25HT-M4

Specifications

Concentricity error	≤ 0.5 µm		
Cladding major diameter	125 ± 1 μm		
Mode field diameter	3.4 ± 0.4 µm @ 1310 nm		
	4.0 ± 0.3 μm @ 1550 nm		
Fiber cut-off wavelength	≤ 1280 nm		
Attenuation	≤ 50 dB/km @ 1310 nm		
	≤ 35 dB/km @ 1550 nm		
Bending loss	≤ 0.01 dB		
	@ 1550nm, R5 mm x 10turns		
Proof test level	≥ 2%		
Coating structure	UV curable acrylate resin		
Coating diameter	245 ± 15 μm		
Minimum bending radius *	R5 mm		

^{*}Optical characteristics are assured.

Product list

Product	Specification number		
		ID	Rev
TEC13-15-U25HT-M4	B-13D0086-18-	1	1



Optical Fiber Division

1440, Mutsuzaki, Sakura, Chiba 285-8550, Japan

http://www.fujikura.co.jp/ optodevice@jp.fujikura.com

Specifications are subject to change without prior notice