

**FutureGuide™-BIS-B-200**
**Compliant with ITU-T G.657.A2**

In urban optical fiber networks, effective utilization of space is crucial, often requiring the installation of high-density cables with small diameters and/or higher count. This demand is particularly increasing in access networks.

To meet this demand, we offer FutureGuide™-BIS-B-200, which utilizes an advanced fiber coating technology to achieve a coating diameter of 200 μm. This fiber maintains excellent bending performance while reducing the cross-sectional area by approximately 40%. FutureGuide™-BIS-B-200 not only allows for more efficient utilization of available space but also contributes significantly to cost reduction in cable manufacturing, transportation, and installation.

**Features**

- Reduced coating diameter down to 200 μm
- Superior macro-bending performance complying with ITU-T G.657.A2.
- Zero(low)-water peak attenuation complying with ITU-T G.652.D

**Customer's advantages**

- Enables design of reduced-diameter and high fiber-count cable.
- Helps flexible wiring and to save wiring space and installation time with easy handling.
- Helps full-band CWDM by its zero(low)-water peak technology.

**Optical Characteristics**

Attenuation	
Attenuation coefficient at 1310 nm	≤ 0.35 dB/km
Attenuation coefficient at 1383 nm	≤ 0.34 dB/km *1
Attenuation coefficient at 1550 nm	≤ 0.20 dB/km
Attenuation coefficient at 1625 nm	≤ 0.22 dB/km
Attenuation vs. wavelength *2	
1285 – 1330 nm ref. λ of 1310 nm	α ≤ 0.03 dB/km
1525 – 1575 nm ref. λ of 1550 nm	α ≤ 0.02 dB/km
Macro-bending loss	
Φ=30 mm, 10 turns at 1550 nm	≤ 0.03 dB
Φ=30 mm, 10 turns at 1625 nm	≤ 0.1 dB
Φ=20 mm, 1 turn at 1550 nm	≤ 0.1 dB
Φ=20 mm, 1 turn at 1625 nm	≤ 0.2 dB
Φ=15 mm, 1 turn at 1550 nm	≤ 0.5 dB
Φ=15 mm, 1 turn at 1625 nm	≤ 1.0 dB

Cut off wavelength	
Cable cut-off wavelength	≤ 1260 nm
Chromatic dispersion	
Chromatic dispersion coefficient at 1285-1330 nm	≤ 3.5 ps/(nm·km)
Chromatic dispersion coefficient at 1550 nm	13.3 - 18 ps/(nm·km)
Chromatic dispersion coefficient at 1625 nm	17.2 - 22 ps/(nm·km)
Zero-dispersion wavelength	1300 - 1324 nm
Zero-dispersion slope	0.073 - 0.092 ps/(nm <sup>2</sup> ·km)
Polarization mode dispersion (PMD) *3	
Uncabled fiber PMD coefficient	≤ 0.1 ps/√km
Link design value PMD <sub>α</sub>	≤ 0.08 ps/√km

\*1. The attenuation at 1383nm after hydrogen aging in accordance with IEC60793-2-50

\*2. The attenuation within the specified wavelength range is limited to a difference of α or less compared to the reference wavelength (ref. λ).

\*3. This characteristic is guaranteed only in a virtually tension-free condition.



Contact us

**Structural Characteristics**

Mode field diameter at 1310 nm	8.6 ± 0.4 μm
Cladding diameter	125.0 ± 0.7 μm
Coating diameter (colored)	190 - 210 μm
Core concentricity error	≤ 0.5 μm
Cladding non-circularity	≤ 0.7 %
Coating-Cladding concentricity	≤ 10 μm
Fiber curl radius	≥ 4.0 m

**Mechanical Characteristics**

Proof test *4	≥ 1.5 % (150 kpsi or 1.0 GPa)
Dynamic stress corrosion susceptibility parameter (n <sub>d</sub> )	≥ 20
Coating strippability F	0.4 N ≤ F ≤ 8.9 N

\*4. The product is subjected to tensile testing throughout its entire length.

**Environmental Characteristics**

	Attenuation Change at 1310, 1550, 1625 nm
Temperature dependence -60 to 85 °C	≤ 0.05 dB/km Ref. temp. 23 °C
Water immersion at 23 °C ± 2 °C	≤ 0.05 dB/km
Dry heat at 85 °C ± 2 °C	≤ 0.05 dB/km Ref. temp. 23 °C
Damp Heat 85 °C at 85 %R.H.	≤ 0.05 dB/km Ref. temp. 23 °C

**Performance Characteristics**

	Typical value
Zero dispersion wavelength	1315 nm
Zero dispersion slope	0.086 ps/(nm <sup>2</sup> ·km)
Effective group index of refraction N <sub>eff</sub> at 1310 nm	1.4681
Effective group index of refraction N <sub>eff</sub> at 1550 nm	1.4687
Effective group index of refraction N <sub>eff</sub> at 1625 nm	1.4691

Note: This document is published for your reference purpose only and the specifications for commercial purpose will be issued upon agreement with customers.

Note: If you require more detailed information, please contact us by scanning the QR code below.



Contact us